


Lock-Tile Flexible PVC Tiles




**Made in USA!
Made from Recycled
Materials.**



Easy To Install!

Install in just hours, glue in areas with forklift traffic.



Very Durable!

Easy to clean; resistant to most chemicals



30 Year Guarantee!

Will never rot or be damaged by leaks or floods.

Free Samples & Quotes upon request!

Black & Dark Grey colors ship quickly!

Quantity Discounts Available!

www.elitegaragefloors.com | 361-906-0863


Lock-Tile Flexible PVC Tiles

Coin 4.5MM Thickenss in Black or Grey


Coin & Smooth 7MM Interlocking Tiles

19-5/8" x 19-5/8" x 7MM


Available Colors for 7MM




Black




Dark Grey




Light Grey




Brown




Tan




Blue




Purple




Red




Light Green



Green



Yellow



White



Smooth



Coin



Lock-tile®
INTERLOCKING FLOOR TILES
EVERTILE FLOORING CO., INC.

| Technical Specification | Standard | Units of Measurement | Lock-tile® Coin | Lock-tile® Smooth |
|-------------------------|---|--|-------------------------------------|----------------------|
| Tile Dimension | | | 19 5/8" x 19 5/8" | 19 5/8" x 19 5/8" |
| Thickness | | mm | 6.75 | 6.75 |
| Material | | | PVC SGI | PVC SGI |
| Hardness | ASTM 2240 | SHORE A | 90 | 90 |
| Moisture Absorption | ASTM D-0471 | | Less than 3% by weight (72H @ 70°F) | |
| Specific Gravity | ASTM D-792 | | 1.37 (+/- 0.02) | 1.37 (+/- 0.02) |
| Tensile Strength | ASTM D-638 | psi | 2700 | 2700 |
| 100% Modulus | ASTM D-412 | psi | 2700 | 2700 |
| Dielectric Strength | ASTM D-149-97A | KV | Exceeded 45 | Exceeded 45 |
| Flame Speed | DIN51960 | | Class 1 | Class 1 |
| Fire Resistance | ANSI/ASTM E648 979 | A/NFPA 235 1995 Critical Rad Flux | Class 1 | Class 1 |
| Electrical Resistance | DIN 53582 | Ohms | 1 X 10 ¹⁴ | 1 X 10 ¹⁴ |
| Anti-Slip | ASTM D-2047 | Static coefficient of friction, conforms to Americans with Disability Act (ADA) specifications | | |
| Dimensional Stability | NF EN404 | % | 0.40 | 0.40 |
| Chemical Resistance | DIN 51958 | Hydrochloric Acid ▶ 100% Ethanol ▶ 95% Nitric Acid ▶ 70% Sulfuric Acid ▶ 95% Also resistant to water, mold, mildew, oil, gasoline and most solvents | | |
| Standard Indention | NF EN 433 | inch | | |
| > Under Load | | | 1.57 | 1.57 |
| > Load Removal | | | 0.20 | 0.20 |
| Sound Absorption | db | | Up to 40db | Up to 40db |
| Testing | Passes ASTM E 652-93 , Specific Optical Density of smoke generated by solid materials, also Referenced as NFPA 258 . | | | |
| | Passes ASTM E 648-97A , Critical Radiant Flux of Floor Covering Systems using a radiant heat Energy source, also referred as NFPA 253 and FTM Standard 372 . | | | |

Distributed by Elite Xpressions
www.elitegaragefloors.com | 361-906-0863